



TECHNICAL SPECIFICATIONS

STACBOND FR
fire retardant ACP

VER: 001 / 2026

ecogreen
STACBOND

PANEL PHYSICAL SPECIFICATIONS

Total panel thickness (mm)	Panel weight (kg/m ²)
	Thickness of lacquered face of 0.5 (mm)
4	7.3±8%

ALUMINIUM ALLOY

ecogreen

VALUE

NORM

Visible face	5005	UNE-EN 573-3
Hidden face	3105/3005	UNE-EN 573-3

SHEET DIMENSIONS

UNITS

VALUE

Width (min./max.)	mm	800/2000**
Length (min./max.)	mm	2000/6000**
Thickness tolerance	mm	-0.15/+0.1
Width tolerance	mm	-0/+2
Length tolerance	mm	-0/+10
Squareness (diagonal tolerance)	mm	±3
Protective film width tolerance	mm	0;-5

TECH. SPECS. OF THE PANEL

UNITS

VALUE

NORM

Peeling	N/mm	≥9.80	ASTM D903-98 (2004)
Rigidity (EI)	kNcm ² /m	2610	DIN 53293
Resistant module (W)	cm ³ /m	1.496	
Acoustic insulation Rw (C;Ctr)	dB	33 (-1;-4)	ISO 717-1:2013
Sound reduction Rw	dB	29.9±1.30	
Thermal resistance (R)	m ² K/W	0.014	
Thermal conductivity	W/m ² K	0.448	UNE-EN ISO 12567-1
Thermal transmittance (U)	W/m ² °C	5.67	
Thermal expansion (α)	mm/m (100°)	1.66	UNE-EN ISO 10545:2019
Operating temperature	°C	-50/+80	

CORE SPECIFICATIONS

FR

UNITS

VALUE

NORM

Density	g/cm ³	1.50±0.15	
Fire reaction		B _s sl-d0	UNE-EN 13501-1:2018

ALUMINIUM TECH. SPECIFICATIONS

UNITS

VALUE

NORM

Alloy		3005A	3005A	UNE-EN 573-3
		H42/H44	H42/H44	UNE-EN 515
Modulus of elasticity (E)	N/mm ²	70 000	70 000	EN 485-2
Proof stress (Rp 0.2)	N/mm ²	≥ 80	≥ 110	EN 485-2
Tensile strength (Rm)	N/mm ²	125≥ Rm≥ 205	130≥ Rm≥ 215	EN 485-2
Elongation (A50)	%	≥ 3	≥ 4	EN 485-2
Density (ρ)	kg/m ³	2,700	2,700	EN 485-2
Thermal expansion (α)	mm/m (100°)	2.36	2.36	UNE-EN ISO 10545:2019

* Aluminium alloy 5005 available by customer request.

** Check with us for other dimensions.